



Ken Bi

cat. C

30% PL; 25%PC; 15% CO; 15% VI; 10% WO; 5% LI
Flame retardant - 60.000 Martindale



004 avorio



003 gesso



005 sabbia



015 corda



017 tortora



019 caffè



012 vinaccia



016 zafferano



007 bosco



008 antracite

Technical details

Composition	30% PL; 25% PC; 15% CO; 15% VI; 10% WO; 5% LI
Weight	Gr./ml. 930
Abrasion test	Martindale - ISO 12947-2: 60.000 rubs
Lightfastness	ISO 105-B02: 4/5
Pilling	ISO 12945-2: 4
Flame retardant	BS 5852-1:1979 CIGARETTE CALIFORNIA BULLETIN TB 117:2013