



## Saten

cat. B

65% PU - 35% CO  
Flame retardant - 100.000 Martindale

R2350

R2353

R2351

R2340

R2349

R2354

M2561

# Saten

## Technical details

Composition	65% PU - 35% CO
Weight	Gr./m <sup>2</sup> 510
Abrasion test	Martindale - 12974-1-2/00: 100.000 rubs
Lightfastness	EN ISO 105-B02 4/5 blue scale
Flame retardant	UNI 9175 CLASS 1 IM EN 1021:2014-1-2 BS 5852 PART 0 CIGARETTE TEST BS 5852 PART 1 MATCH TEST BS 5852-2006 SECT 11, IGNITION CRIB 5 IMO Res MSC.307(88)-(2010 FTP Code) Annex 1 part 8 cert nr. MED 0497/802
Feature	ORTHO PHTHALATE FREE