



Cleo

95% WV – 5%PA
Flame retardant - 60.000 Martindale




pearl




angora




linen



rock




carbon



pepper



water




salbei



walnut



gold



lemon




azalee



flamingo



passion



peach



lampion



marone



magma



sky



ocean



anthrazit



ink



lanoso



coal

Technical details

Composition	95% WV – 5%PA
Weight	Gr./m ² 690
Abrasion test	Martindale - ISO 12947-2: 60.000 rubs
Lightfastness	ISO 105-B02: 5
Pilling	ISO 12945-2: 4/5
Fastness to rubbing	ISO 105-X12: Wet 4/5 Dry 4/5
Flame retardant	UNI 9175 1IM CAL TB 117 - 2013 DIN EN 1021- 1/-2 BS 5852 part 1: 1979 ÖNORM B1/Q1
Environment	NATURAL RENEWABLE MATERIAL IWTO GUIDELINES FOR WOOLSHEEP WELFARE