


# Hestan

cat. B

100% polyester FR  
Flame retardant - 60.000 Martindale



7035.11



7035.10



7035.29




7035.04



7035.21



7035.20



7035.01



7035.19



7035.17




7035.12



7035.22



7035.13




7035.09



7035.18



7035.27



7035.03



7035.24



7035.02



7035.25



7035.28



7035.16



7035.14



7035.15



7035.08



7035.07



7035.05



7035.26



7035.06



Technical details

Composition	100% polyester FR
Weight	Gr./ml. 570
Abrasion test	Martindale - ISO 12947-2: 60.000 rubs
Lightfastness	ISO 105-B02: 6/7
Pilling	ISO 12945-2: 4/5 ASTM D3511: 4,5
Fastness to rubbing	ISO 105-X12: Wet 5 Dry 5 AATC 8: Wet 5 Dry 5
Flame retardant	EN 1021/1-2 BS 5852, crib 5 NF P 92/503-507, M1 DIN 4102, B1 IMO 2010 FTP, part 8 UNI 9175, classe 1 Cal TB 117-2013
Environment	CERTIFIED TO OEKO-TEX® STANDARD 100